

PRODUCT DESCRIPTION

DURA♦SKRIM® NQ36B is a highly flexible geomembrane, reinforced with a closely knit 9x9 weft inserted polyester scrim fully encapsulated between two layers of highly UV stabilized polypropylene. Exceptional flexibility is achieved by incorporating high levels of ethylene propylene rubber into polypropylene along with a dense scrim reinforcement, resulting in excellent dimensional stability and physical properties.

DURA♦SKRIM® NQ-Series polypropylene membranes do not contain plasticizers that can leach out and hinder long-term flexibility and performance. DURA♦SKRIM® NQ36B provides outstanding resistance to environmental stress cracking even in elevated temperatures and chemical environments. DURA♦SKRIM® NQ-Series geomembranes are produced in the color black as standard, and are available in other custom manufactured colors with minimum order quantity requirements.

PRODUCT USE

DURA♦SKRIM® NQ36B is used in a wide variety of exposed and buried applications that require a unique combination of mechanical toughness, excellent flexibility, and environmental stress cracking resistance. The outer plies provide outstanding heat welding characteristics valued by Installers and fabricators. DURA♦SKRIM® NQ36B polypropylene geomembrane offers a high-friction angle reducing concerns for side slope stability.

DURA♦SKRIM® NQ36B meets the physical property values as stated in GRI test method GM18, and is certified under the NSF/ANSI Standard 61, Drinking Water System Components – Health Effects.

SIZE & PACKAGING

DURA♦SKRIM® NQ36B is available in a variety of widths and lengths to meet the project requirements. Large diameter mill rolls are available to assure an efficient seaming process. Factory welded panels are produced in a controlled environment and are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time saving installation.



Waste Containment Liner

PRODUCT

PART

DURA♦SKRIM NQ36B

APPLICATIONS

- | | |
|-------------------------|-------------------------|
| Waste Lagoon Liners | Remediation Covers |
| Floating Covers | Landfill Caps |
| Fish Hatchery Liners | Farm Pond Liners |
| Modular Tank Liners | Canal Liners |
| Tunnel Liners | Disposal Pit Liner |
| Remediation Liners | Water Containment Ponds |
| Earthen Liners | Heap Leach Liner |
| Interim Landfill Covers | |

DURA♦SKRIM® NQ36B

REINFORCED FLEXIBLE POLYPROPYLENE – NSF/ANSI STANDARD 61 CERTIFIED

PRO-FORMA DATA SHEET

		DURA♦SKRIM® NQ36B			
		IMPERIAL		METRIC	
PROPERTIES	TEST METHOD	MINIMUM	TYPICAL	MINIMUM	TYPICAL
APPEARANCE		Black		Black	
THICKNESS	ASTM D5199	32 mil	36 mil	0.81 mm	0.91 mm
WEIGHT	ASTM D751	150 lbf/msf	155 lbf/msf	732 g/m ²	757 g/m ²
CONSTRUCTION		9x9-1000 Denier PET scrim reinforced polypropylene			
TONGUE TEAR STRENGTH	ASTM D5884	90 lbf	130 lbf	400 N	578 N
GRAB TENSILE AT BREAK	ASTM D7004	200 lbf	225 lbf	890 N	1001 N
TENSILE ELONGATION AT BREAK	ASTM D7004	22 %	30 %	22 %	30 %
PUNCTURE RESISTANCE	ASTM D4833	80 lbf	95 lbf	356 N	423 N
HYDRAULIC CONDUCTIVITY		1.39 x 10 ⁻⁹ cm/sec			
MAXIMUM STATIC USE TEMPERATURE		180° F		82° C	
MINIMUM STATIC USE TEMPERATURE		-70° F		-57° C	

PRO-FORMA SHEET CONTENTS: The data listed in the Pro-Forma data sheet is representative of initial production runs. These values may be revised at anytime without notice as additional test data becomes available.



D DURA♦SKRIM® NQ36B is a highly flexible geomembrane, reinforced with a closely knit 9x9 weft inserted polyester scrim fully encapsulated between two layers of highly UV stabilized polypropylene. Exceptional flexibility is achieved by incorporating high levels of ethylene propylene rubber into polypropylene along with a dense scrim reinforcement, resulting in excellent dimensional stability and physical properties.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. RAVEN INDUSTRIES MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.ravenefd.com

RAVEN ENGINEERED FILMS
P.O. Box 5107 Sioux Falls, SD 57117-5107
Ph: +1 (605) 335-0174 • TF: +1 (800) 635-3456

efdsales@ravenind.com
www.ravenefd.com

