

PROPERTIES	TEST METHOD	FEEDPRO™ A5WB	
		Imperial	Metric
APPEARANCE		White/Black	
THICKNESS, NOMINAL	ASTM D5199	5 mil	0.125 mm
WEIGHT		25 lbs/MSF	122 g/m ²
CONSTRUCTION	ASTM D5199	Co-Extruded 3-Layer Film	
*TENSILE STRENGTH lbf/in. (N/cm)	ASTM D882	28 lbf	49 N
*TENSILE ELONGATION	ASTM D882	950%	950%
ELMENDORF TEAR TEST, MD	ASTM D1922	1800 g	1800 g
PUNCTURE RESISTANCE	ASTM 4833	14 lbs	62 N
OPACITY		100%	100%
MAXIMUM USE TEMPERATURE		180°F	82°C
MINIMUM USE TEMPERATURE		-70°F	-57°C

*Tests are an average of machine and transverse directions.



FeedPro™ A5WB Silage Covers consist of U.V. stabilized white/black tri-layer polyethylene. The bright white top layer provides excellent protection from ultraviolet rays and reflects sunlight to minimize heat build-up and help prevent spoilage. The reverse side consists of a black opaque layer of puncture resistant polyethylene to prevent light transmission from reaching the pile. Readily available in all the extra large hard-to-find sizes.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. RAVEN INDUSTRIES MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.RavenEFD.com



Engineered Films Division
 P.O. Box 5107
 Sioux Falls, SD 57117-5107
 Ph: (605) 335-0174 • Fx: (605) 331-0333

Toll Free: 800-635-3456
 Email: efdsales@ravenind.com
www.ravenefd.com
 1/13 EFD 1114



Scan QR Code to download current technical data sheets via the Raven website.