

PRODUCT DESCRIPTION

HydraFlex™ PP30 is an exceptionally flexible geomembrane, achieved by incorporating high levels of ethylene propylene rubber into polypropylene. HydraFlex™ polypropylene membranes contain no plasticizers that can leach out and hinder long-term flexibility and performance. HydraFlex™ fPP-Series provides outstanding resistance to environmental stress cracking even at elevated temperatures and in addition to aggressive chemical environments.

PRODUCT USE

HydraFlex™ PP30 is used in a wide variety of applications that require a unique combination of mechanical toughness, exceptional flexibility and environmental resistance. Raven's polypropylene geomembranes meet the requirements of GRI-GM18 standard specifications for flexible polypropylene non-reinforced geomembranes.

HydraFlex™ fPP-Series provides a high-friction angle to increase side slope stability. A low coefficient of thermal expansion significantly reduces wrinkling in a wide range of temperatures. HydraFlex™ PP30 may be considered for containment of leachates from typical Municipal Solid Waste per EPA 9090 testing in addition to black liquor from paper manufacturing.

SIZE & PACKAGING

HydraFlex™ PP30 is available as a custom run product with minimum order requirements. All panels are accordion folded every 5 feet, and tightly rolled onto a heavy-duty core for ease of handling and time-saving installation.



Pond Liner

PRODUCT

PART

HYDRAFLEX™ PP30

APPLICATIONS

- | | |
|-------------------------|--------------------|
| Canal Linings | Evaporation Ponds |
| Decorative Ponds | Mine Tailing Ponds |
| Landfill Caps | Fire Ponds |
| Waste Lagoon Ponds | Remediation Liners |
| Golf Course Water Traps | Farm Ponds |
| Brine Ponds | Fish Hatcheries |
| Aquaculture | |

HYDRAFLEX™ PP30

FLEXIBLE SMOOTH POLYPROPYLENE

		HYDRAFLEX™ PP30			
		IMPERIAL		METRIC	
PROPERTIES	TEST METHOD	MINIMUM	TYPICAL	MINIMUM	TYPICAL
APPEARANCE		Black			
THICKNESS, AVERAGE	ASTM D5199	27 mil	29 mil	0.69 mm	0.74 mm
WEIGHT		120 lbs/msf	137 lbs/msf	586 g/m ²	669 g/m ²
TENSILE STRENGTH AT BREAK	ASTM D6693	62 ppi	69 ppi	109 N/cm	121 N/cm
TENSILE ELONGATION AT BREAK	ASTM D6693	700 %	900 %	700 %	900 %
TEAR RESISTANCE	ASTM D1004	10 lbs	11.5 lbs	44 N	51 N
PUNCTURE RESISTANCE	ASTM D4833	25 lbs	34 lbs	111 N	151 N
MULTIAXIAL ELONGATION AT BREAK	ASTM D5617	120 %	200%	120 %	200 %
CARBON BLACK (BLACK LAYERS ONLY)	ASTM D4218	2.0 - 3.5 %	2.5 %	2.0 - 3.5 %	2.5 %
HYDRAULIC CONDUCTIVITY		1.5 x 10 ⁻⁹ cm/sec			
MAXIMUM STATIC USE TEMPERATURE		180° F		82° C	
MINIMUM STATIC USE TEMPERATURE		-70° F		-57° C	



HydraFlex™ PP30 is an exceptionally flexible geomembrane, achieved by incorporating high levels of ethylene propylene rubber into polypropylene. HydraFlex™ polypropylene membranes contain no plasticizers that can leach out and hinder long-term flexibility and performance. HydraFlex™ fPP-Series provides outstanding resistance to environmental stress cracking even at elevated temperatures and in addition to aggressive chemical environments.

HydraFlex™ PP30 may be considered for containment of leachates from typical Municipal Solid Waste per EPA 9090 testing in addition to black liquor from paper manufacturing.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. RAVEN INDUSTRIES MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.RavenEFD.com

RAVEN ENGINEERED FILMS

P.O. Box 5107 Sioux Falls, SD 57117-5107
Ph: +1 (605) 335-0174 • TF: +1 (800) 635-3456

© 2017 RAVEN INDUSTRIES INC. All rights reserved.

efdsales@ravenind.com
www.ravenefd.com



031717 EFD 1391